

ABSTRACT OF THE DISCLOSURE

Aphenolicmoldingcompositioncontaining40to100parts
byweightofinorganicfiber,30to90partsbyweightofnatural
silica powder with a mean particle size of from 20 to 150 μ m,
5 and 1 to 15 parts by weight of a rubber component, as main
components, in 100 parts by weight of resol-based phenolic
resin. Preferably, the inorganic fiber contains 50% or more
by weight of glass fiber. Further preferably, the natural
silica powder is shaped like pulverized powder. A pulley is
10 molded of a phenolic molding composition defined above.